



CHARACTERISTICS

- Silane-/siloxane mixture, dissolved in aromatic free and odourless organic solvent.
- Reacts with air humidity or with the moisture present in the surface. Owing to this reaction, a stable insoluble final product forms, which settles as silicone resins system on the pore walls. The surface obtains a permanent water-repellent effect with retention of water vapour permeability.
- Also protects the surface against frost and moss formation.

APPLICATIONS

- Especially developed for making facing bricks, bricks and plasterwork water-repellent.

TECHNICAL CHARACTERISTICS

Appearance	Transparent
Weight % solid matter	9 %
Density	0,80 g/cm ³
Pearling effect	Visible after 4 - 5 h
Flash point	63°C
Quantity	1 - 1.5 l/m ² , depending of the porosity of the surface
Application temperature	+10°C - +30°C.
Shelf life, stored in closed container and frost free environment. Temperatures > +30° must be avoided. Protect packaging against sunlight.	12 months

PACKING

Bottle 1 l - 576 bottles/pallet
Bidon 5 l - 120 bidons/pallet
Bidon 25 l - 26 bidons/pallet

METHOD OF USE

Preparation

The surface must first be cleaned with water under pressure, by sand blasting or chemical treatment. Use suitable mortar to repair damaged surface. Cracks or tears wider than 0.15 mm must be filled.

Parafuge SX29 can only be applied to clean, dry to slightly moisture surface.

Application

- Tools: low-pressure pistol and roll or brush
- When applying you must make sure that a liquid curtain always flows over the surface so that it is completely saturated.
- Start the treatment at a strip of 40 cm in a forward and back motion.
- Apply at a temperature between +10°C and +30°C. Work as much as possible in shade to keep the product from drying quickly.
- ATTENTION: You must protect the surfaces not to be treated.

Cleaning

Equipment with white spirit

SAFETY

Safety data sheet available on request.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.