



CHARACTERISTICS

- Pasty construction adhesive
- Based on synthetic elastomeres and solvents,
- Non-aggressive towards polystyrene or the silvering of mirrors.
- Has an excellent initial grip
- Highly water resistant
- Keeps its elasticity

APPLICATIONS

- Suitable for the bonding of mirrors, material in polystyrene or expanded polyurethane.
- Also suitable for the bonding of concrete, masonry, plaster, wood, metal, PVC etc.

TECHNICAL CHARACTERISTICS	
Consistency	Paste
Base	Synthetic elastomere in a solvent
Solid contents	75%
Density	1,26 g/ml
Shelf life, in the original packing in dry conditions between +5°C - +25°C	Min. 12 months
Processing temperature	+15°C - +25°C
Consumption	15 meter per cartridge (cords of 5 mm)
Open time at 20°C	10 - 20 min
Temperature resistance	-15°C - +80°C

PACKING AND COLOURS
25 cartridges of 290 ml/box - 48 boxes/pallet
Light beige

METHOD OF USE

Preparation

The surface has to be clean and free from grease.

Application

- Apply in cords of min. 5 mm diameter, with a distance of 10 cm max. between the cords.
- Press onto the other surface, remove it, wait a few minutes in order to let the solvents evaporate (5 to 8 min for light material, 8 to 15 min for heavy material, up to 30 min). Apply again and press hard (Transfer method).
- The object has to be positioned with great precision, as the adhesion is immediate. It is possible to adjust the position by 2 to 3 mm within 5 min after assembling.
- Heavy material of more than 8 kg/m³ must be supported during 8 to 15 hours. Good adhesion is obtained after 1 hour, but you have to wait 24 to 48 hours before submitting the support to tensile force.
- **Paracol Miroseal SBR** will level out any defective flatness of the support up to 3 mm max.

Cleaning

With water

SAFETY

Please refer to safety data sheet which is available on request.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.

LIMITATIONS

Do not use on a surface completely immersed in water.

TECHNICAL APPROVALS



* Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.